

Technical data sheet

Reparation tape mdm® Ventia Finger-Lift

Property	Test method	Unit	Result	Tolerance	
				Min.	Max.
Carrier			Nonwoven PP, stabilized UV		
Adhesive					
Length	EN 1848-2	m	25	-0	+0,5
Width	EN 1848-2	mm	50	-0,5%	+1,5%
Straightness	EN 1848-2	-	+	-	-
Shear Strength	EN 12317-2	N/50 mm	75	-15%	+15%
Peel strength	EN 12316-2	N/50 mm	4,5	-15%	+15%
dimensional stability	EN 1107-2	%	1	-	-
temperature resistance	-	°C	from -30 to +80	-	-
installation temperature		°C	from 0 to 40		
UV Resistance	EN 1297	-	max. 3 months	-	-

Cieszyn, 13. 01. 2014 r.

(place, date of issue)

Bank Zachodni WBK S.A., SWIFT: WBKPPLPP
IBAN: PL 83 1090 1782 0000 0001 0868 0742 (PLN)
IBAN: PL 20 1090 1782 0000 0001 0875 6954 (EUR)
NIP: 548-23-52-532, REGON 072802798
Numer KRS 0000296371, Sąd Rejonowy w Bielsku-Białej,
VIII Wydział Gospodarczy Krajowego Rejestru Sądowego
Wysokość opłaconego kapitału zakładowego: 5 000 000 PLN