

Technical data sheet**Vapour barrier mdm[®] Verso Top 120 WK**

Characteristic	Test method	Unit	Value	Tolerance	
				Min.	Max.
Resistance to water penetration	EN 1928 Method A	-	requirements met	-	-
Tensile properties: maximum tensile force	EN 12311-2	N/50 mm	MD ≥ 120	-	-
			CD ≥ 70	-	-
Tensile properties: elongation	EN 12311-2	%	≥50	-	-
Resistance to tearing (nail shank)	EN 12310-1	N	MD ≥ 95	-	-
			CD ≥ 105	-	-
Resistance to strike (with styrofoam base)	EN 12691	mm	NPD	-	-
Connection resistance (Astat tape used)	EN 12317-2	N/50 mm	NPD	-	-
Water vapour transmission properties: Sd	EN 1931	m	≥ 3,5	-	-
Water vapour resistance	EN 1931	[(m ² x s x Pa)/kg]	NPD	-	-
Water vapour transmission properties (after artificial ageing)	EN 1296 i EN 1931	-	requirements met	-	-
Resistance to deformation under weight	No reference – non profiled merchandise				
Alkalis resistance	No reference – merchandise has no contact with most concrete				
Reaction to fire	EN 13501-1	class	F	-	-
Length	EN 1848-2	m	50	-0	+0,5
Width	EN 1848-2	m	1,50	-0,005	+0,005
Thickness	EN 1849-2	mm	0,45	-0,1	+0,1
Mass per unit area	EN 1849-2	g/m ²	120	-15	+15
Straightness	EN 1848-2	-	requirements met	-	-
Visible defects	EN 1850-2	-	none	-	-

Bielsko Biała, 18.10.2018
 (place and date)